



NATURE SCIENCES

Received: January 2009
Accepted: March 2009
Series : 3A
ISSN : 1308-7304
© 2009 www.newwsa.com

Adnan Kurt
Kadir Demirelli
University of Firat
adnankurt@firat.edu.tr
Elazig-Turkey

**SYNTHESIS AND CHARACTERIZATION OF BLOCK COPOLYMERS OF
ETHYL METHACRYLATE WITH STYRENE VIA ATRP**

ABSTRACT

The homopolymer of ethyl methacrylate and diblock and triblock copolymer with styrene were accomplished by atom transfer radical polymerization method. Temperature studies indicated that the polymerizations occurred smoothly in bulk at 110°C and 130°C for ethyl methacrylate and Styrene. Of all polymers were characterized by FT-IR, ¹H-NMR, UV-VIS and DSC techniques. The percentage of styrene units in the diblock and triblock copolymers were obtained as 68 and 21 (by %), respectively. The T_g values for poly(EMA), poly(EMA-b-St) diblock and poly(EMA-b-St-b-EMA) triblock copolymer were determined as 73°C, 97°C and 78°C, respectively. The results obtained from GPC chromatograms showed that the polymerizations were controlled/living. The average molecular weight (M_n) and the molecular weight distribution of homo, diblock and triblock copolymers were found as 3100, 29300, 40000 and as 1,14, 1,17, 1,96, respectively.

Keywords: ATRP, Block Copolymerization, Synthesis, Characterization, Ethyl Methacrylate, Styrene

**ATRP METODUYLA ETİL METAKRİLATİN STİREN İLE BLOK KOPOLİMERLERİNİN
SENTEZİ VE KARAKTERİZASYONU**

ÖZET

Etilmetakrilatin homopolimeri ve Stiren ile olan diblok ve triblok kopolimerleri atom transfer radikal polimerizasyon yöntemi ile gerçekleştirildi. Etilmetakrilat ve stirenin polimerizasyonu için gerekli sıcaklıkların sırasıyla 110°C ve 130°C olduğu yapılan sıcaklık çalışmalarından tespit edildi. ATRP şartlarında sentezlenen polimerler FT-IR, ¹H-NMR, UV-VIS ve DSC teknikleri ile karakterize edildi. Stiren birimlerinin diblok ve triblok kopolimer içindeki oranları sırasıyla %68 ve %21 olarak belirlenirken poly(EMA), poly(EMA-b-St) diblok ve poly(EMA-b-St-b-EMA) triblok kopolimeri için camsı geçiş sıcaklıklarını 73°C, 97°C ve 78°C olarak ölçüldü. GPC kromatogramlarından elde edilen sonuçlara göre polimerizasyonların kontrollü-yaşayan karakterli olduğu belirlendi. Sayıca ortalama molekül ağırlıkları ve molekül ağırlık dağılımları sırasıyla 3100, 29300, 40000 ve 1,14, 1,17, 1,96 olarak tespit edildi.

Anahtar Kelimeler: ATRP, Blok Kopolimerizasyon, Sentez, Karakterizasyon, Etil Metakrilat, Stiren